

Alumina Balls 92 Series (grinding media)

Alumina ball is made of commercial grade alumina (α aluminium oxide) by cool isostatic pressing and high temperature (e.g. 1540°C) kiln firing & sintering.

Data Sheet

Al ₂ O ₃	:	92% min.
Fe ₂ O ₃	:	0.25% max.
Mohs hardness	:	9
Water absorption	:	0.02% max.
Bulk density	:	3.60 g/cm ² min.
Wear loss	:	0.15‰ max.
Color	:	white

Packing

25 KGs in one pp bag,
40 bags on one pallet.
Other custom packing is
available upon
customers' request.



Delivery

15 days upon order confirmed and down payment received or L/C arrived.

Manufacturer

HuaMing Alumina Technology Ltd.

March 2, 2009