

## Alumina Balls 92 Series (grinding media)

Alumina ball is made of commercial grade alumina ( $\alpha$  aluminium oxide) by cool isostatic pressing and high temperature (e.g. 1540°C) kiln firing & sintering.

### Data Sheet

|                                |   |                             |
|--------------------------------|---|-----------------------------|
| Al <sub>2</sub> O <sub>3</sub> | : | 92% min.                    |
| Fe <sub>2</sub> O <sub>3</sub> | : | 0.25% max.                  |
| Mohs hardness                  | : | 9                           |
| Water absorption               | : | 0.02% max.                  |
| Bulk density                   | : | 3.60 g/cm <sup>2</sup> min. |
| Wear loss                      | : | 0.15‰ max.                  |
| Color                          | : | white                       |

### Packing

25 KGs in one pp bag,  
40 bags on one pallet.  
Other custom packing is  
available upon  
customers' request.



### Delivery

15 days upon order confirmed and down payment received or L/C arrived.

### Manufacturer

HuaMing Alumina Technology Ltd.

March 2, 2009